

# STEEL CASTINGS - TECHNICAL DATA

## NICKEL BASE ALLOYS



**MONMET**

Monmet helps our customers solve their problems with an unmatched expertise in alloy and process selection.

ALLOY	ASTM SPECIFICATION	CHEMICAL COMPOSITION (Maximum unless range specified)							MINIMUM MECHANICAL PROPERTIES				EQUIVALENT FOREIGN SPECS		CHARACTERISTICS & APPLICATIONS
		C %	Si %	Mn %	Ni %	Cr %	Mo %	Other %	TENSILE STRENGTH (KSI)	YIELD STRENGTH (KSI)	ELONGATION %	HARDNESS (BHN)	BRITISH STANDARD	GERMAN STANDARD	
NICKEL BASE CORROSION RESISTANT ALLOYS	A494: CZ-100	1.00	2.00	1.50	95.00 MIN			Cu 1.25 Fe 3.00	50	18	10	90-140			High resistance to caustic soda & alkaline salts.
	A494: M-35-1	0.35	1.25	1.50	BAL.			Cu 26.0-33.0 Fe 3.50	65	25	25			Excellent resistance to organic acids, alkalis, salt-solutions & sea water. Order M-35-1 or M-30C when weldability is required.	
	A494: M-35-2	0.35	2.00	1.50	BAL.			Cu 26.0-33.0 Fe 3.50	65	30	25				
	A494: M-30-H	0.30	2.70-3.70	1.50	BAL.			Cu 27.0-33.0 Fe 3.50	100	60	10	243-294			
	A494: M-25-S	0.25	3.50-4.50	1.50	BAL.			Cu 27.0-33.0 Fe 3.50 Cb 3.0							
	A494: M-30C	0.30	2.00	1.50	60.00 MIN			Cu 26.0-33.0 Fe 3.5 Cb 3.0	65	32.5	25	125-180			Excellent corrosion resistance to reducing acids (sulphonic, hydrochloric, chlorides) & reducing salts. Applications include pumps, impellers, casings & diffusers.
	A494: N-12MV	0.12	1.00	1.00	61.00 MIN	1.00	26.0-30.0	Fe 4.0-6.0 V 0.20-0.60	76	40	6	180-220			
	A494: N-7M	0.07	1.00	1.00	BAL.	1.00	30.0-33.0	Fe 3.0	76	40	20				This nickel base alloy has properties comparable to the wrought grade: Inconel 600. Resistant to reducing environments. It has excellent temperature strength and creep properties. Used in chemical process, heat treating, power and electronic equipment.
	A494: CY-40	0.40	3.00	1.50	BAL.	14.0-17.0		Fe 11.0	70	28	30				
	A494: CW-12MW	0.12	1.00	1.00	48.00 MIN	15.5-17.5	16.0-18.0	Fe 4.5-7.5 W 3.75-5.25 V 0.20-0.40	72	40	4	220-280			Excellent resistance to oxidizing & mixed acids containing halogens & reducing salts. Applications also include pumps, impellers & casings.
	A494: CW-6M	0.07	1.00	1.00	BAL.	17.0-20.0	17.0-20.0	Fe 3.0	72	40	25				
	A494: CW-2M	0.02	0.80	1.00	BAL.	15.0-17.5	15.0-17.5	Fe 2.0	72	40	20				
A494: CW-6MC	0.06	1.00	1.00	BAL.	3.15-4.50	8.0-10.0	Fe 5.0	70	40	25					
CHROMIUM NICKEL ALLOYS	A560: 50NI-CB	0.10	0.30	0.30	BAL.	47.0-52.0	Fe 1.0 Cb 1.4-1.7	80	50	5				Very good resistance to corrosive environments and elevated-temperatures. Applications include structural members, containers, supports, hangers and spacers.	
	A560: 50CR-50NI	0.10	0.30	0.30	BAL.	48.0-52.0	Fe 1.0 N 0.30	80	50	5					
	A560: 80CR-40NI	0.10	0.30	0.30	BAL.	58.0-62.0	Fe 1.0 N 0.30	110	85						

Monmet offer high nickel based alloys for special corrosion resistant applications.

Nickel Base Corrosion Resistant Alloys  
Chromium Nickel Alloys

Get a Quote

Call 514-788-6007

Email [info@monmet.com](mailto:info@monmet.com)

Visit [www.monmet.com](http://www.monmet.com)

5524 Rue St-Patrick, Suite 202, Montréal QC H4E 1A8